

DN 50–70			
Längd (meter)	Härdare (kg)	Bas (kg)	Total epoxi- vikt (kg)
1	0,14	0,46	0,60
2	0,28	0,92	1,20
3	0,42	1,38	1,80
4	0,55	1,85	2,40
5	0,69	2,31	3,00
6	0,83	2,77	3,60
7	0,97	3,23	4,20
8	1,11	3,69	4,80
9	1,25	4,15	5,40
10	1,38	4,62	6,00
11	1,52	5,08	6,60
12	1,66	5,54	7,20
13	1,80	6,00	7,80
14	1,94	6,46	8,40
15	2,08	6,92	9,00
16	2,22	7,38	9,60
17	2,35	7,85	10,20
18	2,49	8,31	10,80
19	2,63	8,77	11,40
20	2,77	9,23	12,00
21	2,91	9,69	12,60
22	3,05	10,15	13,20
23	3,18	10,62	13,80
24	3,32	11,08	14,40
25	3,46	11,54	15,00

DN 70–100			
Längd (meter)	Härdare (kg)	Bas (kg)	Total epoxi- vikt (kg)
1	0,18	0,62	0,80
2	0,37	1,23	1,60
3	0,55	1,85	2,40
4	0,74	2,46	3,20
5	0,92	3,08	4,00
6	1,11	3,69	4,80
7	1,29	4,31	5,60
8	1,48	4,92	6,40
9	1,66	5,54	7,20
10	1,85	6,15	8,00
11	2,03	6,77	8,80
12	2,22	7,38	9,60
13	2,40	8,00	10,40
14	2,58	8,62	11,20
15	2,77	9,23	12,00
16	2,95	9,85	12,80
17	3,14	10,46	13,60
18	3,32	11,08	14,40
19	3,51	11,69	15,20
20	3,69	12,31	16,00
21	3,88	12,92	16,80
22	4,06	13,54	17,60
23	4,25	14,15	18,40
24	4,43	14,77	19,20
25	4,62	15,38	20,00

DN 100–150			
Längd (meter)	Härdare (kg)	Bas (kg)	Total epoxi- vikt (kg)
1	0,3	1,0	1,30
2	0,6	2,0	2,60
3	0,9	3,0	3,90
4	1,2	4,0	5,20
5	1,5	5,0	6,50
6	1,8	6,0	7,80
7	2,1	7,0	9,10
8	2,4	8,0	10,40
9	2,7	9,0	11,70
10	3,0	10,0	13,00
11	3,3	11,0	14,30
12	3,6	12,0	15,60
13	3,9	13,0	16,90
14	4,2	14,0	18,20
15	4,5	15,0	19,50
16	4,8	16,0	20,80
17	5,1	17,0	22,10
18	5,4	18,0	23,40
19	5,7	19,0	24,70
20	6,0	20,0	26,00
21	6,3	21,0	27,30
22	6,6	22,0	28,60
23	6,9	23,0	29,90
24	7,2	24,0	31,20
25	7,5	25,0	32,50

DN 150–225			
Längd (meter)	Härdare (kg)	Bas (kg)	Total epoxi- vikt (kg)
1	0,51	1,69	2,20
2	1,02	3,38	4,40
3	1,52	5,08	6,60
4	2,03	6,77	8,80
5	2,54	8,46	11,00
6	3,05	10,15	13,20
7	3,55	11,85	15,40
8	4,06	13,54	17,60
9	4,57	15,23	19,80
10	5,08	16,92	22,00
11	5,58	18,62	24,20
12	6,09	20,31	26,40
13	6,60	22,00	28,60
14	7,11	23,69	30,80
15	7,62	25,38	33,00
16	8,12	27,08	35,20
17	8,63	28,77	37,40
18	9,14	30,46	39,60
19	9,65	32,15	41,80
20	10,15	33,85	44,00
21	10,66	35,54	46,20
22	11,17	37,23	48,40
23	11,68	38,92	50,60
24	12,18	40,62	52,80
25	12,69	42,31	55,00

För att uppnå 3mm tjocklek på rör			
Foder	Valsmått	kg/meter	
50-70	7mm	0,6	
70-100	8,5mm	0,8	
100-150	10mm	1,3	
150-225	12mm	2,2	